PAT-NO: JP02001031457A

DOCUMENT-IDENTIFIER: JP 2001031457 A

TITLE: HIGH STRENGTH CONCRETE

PUBN-DATE: February 6, 2001

INVENTOR-INFORMATION:

NAME COUNTRY

TANIMURA, MITSURU N/A
HYODO, HIKOJI N/A
SHIMABUKURO, AKIRA N/A
SHIMOYAMA, YOSHIHIDE N/A

ASSIGNEE-INFORMATION:

NAME COUNTRY

TAIHEIYO CEMENT CORP N/A

APPL-NO: JP11202708

APPL-DATE: July 16, 1999

INT-CL (IPC): C04B028/02

ABSTRACT:

PROBLEM TO BE SOLVED: To provide a <u>high strength concrete</u> having not only small self - shrinkage but also small brittleness coefficient (compression strength/tensile strength).

SOLUTION: This high strength concrete contains a low-heat portland cement, a high-performance water reducing agent or a high performance AE water reducing agent, a fine aggregate and a coarse aggregate, and has ≤ 40 wt.% ratio of water to the cement and ≥ 60 N/mm2 compression strength. A shrinkage-diminishing agent and/or an expanding material is also added to the high strength concrete. Preferably, the ratio of the shrinkage-diminishing agent to the cement is ≤ 2.0 wt.%, and the ratio of the expanding material to the cement is ≤ 10 wt.%.

COPYRIGHT: (C) 2001, JPO